



Green Isofil®

Document Process Data for Injection Moulding**Description** **PP (Polypropylene)****Application** Injection Moulding

Structure	Semicrystalline
General Properties	Hard, good resilience. Low hygroscopicity and good thermal stability.
Barrel Temperature	
	Feed Zone 30 – 50 °C
	Zone 1 160 – 200 °C
	Zone 2 200 – 220 °C
	Zone 3 220 – 240 °C
	Zone 4 220 – 240 °C
	Zone 5 220 – 240 °C
	Nozzle 220 – 240 °C
Melt temperature	220 – 240 °C
Mould temperature	20 – 70 °C
Injection pressure	800 – 1400 bar
Post-pressure	Between 30 and 60% of injection pressure, high post-pressure time
Counterpressure	50 – 200 bar
Injection speed	Medium
Screw speed	Equal to peripheric speed of 1.3 m/s
Metering	0.5 – 4.0 diameters
Cushion	2 – 8 mm, depends on metering and screw diameter
Drying	Not necessary. 1 hour at 70°C if stored in humid place or for aesthetical requirements.
Recycle	100% of regrinded material.
Shrinkage	0.8 – 1.5 %, complete after 40 hours.
Barrel equipment	Standard screw, non-return valve, free-flow nozzle
Quenching	Not necessary to purge with other materials.

Sirmax s.p.a.E.A.R. N° 91334
P.IVA 00168180248
sirmax@sirmax.com**Group Headquarter:**Viale dell'Artigianato, 42
35013 Cittadella (PD) – Italy
Tel. +39 049 9441111 – Fax +39 049 9441112