



Document	ASTM Datasheet
Description	TPO
Grade	Xelter - Tech
Code	
Application	Injection Moulding

Properties	Method	Unit	Value
Physical			
Density at 23°C	ASTM D729	g/cm ³	0,90
Mechanical at 23 °C			
Hardness 3"	ASTM D2240	Shore D	55
Melt Flow Rate (230°C- 2.16 kg)	ASTM D1238	g/10'	5
Flexural Modulus (23°C – 2mm/min)	ASTM D790	MPa	550
Izod Notched (23°C)	ASTM D256	J/m	700
Vicat B50	ASTM D1525	°C	46
Melt Flow Rate (230°C- 2.16 kg)	ASTM D1238	g/10'	5
Processing Conditions			
Melt Temperature Range	°C	210-220-220	
Nozzle	°C	230	
Mold Temperature Range	°C	20-40	
Drying Temperature	°C	Not necessary	
Drying Time	Hour	Not necessary	
Regulations compliance			
RoHS compliance status:	COMPLIANT		
Shelf life			
1 year from production date			

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

The value above is the representative value of the NP standard and may have deviation. It can only be used for selecting materials and shall not be regarded as a material specification and cannot be used for molding designs. Information inserted in this document such as data, statements, representative values, etc. are provided solely for customer convenience. It does not expressly or impliedly guarantee anything regarding the safety or practicability of the (1) materials, (2) products, and/or (3) design that utilizes recommendations or proposals, of Sirmax. Furthermore, nothing in the contents of this document shall have any legal binding effect, and especially, the representative value is simply for reference and is not a minimum value that has legal binding effect.

Whether materials and/or products of Sirmax and/or a design that uses or utilizes Sirmax recommendations or proposals are (is) compatible with individual uses shall be determined solely by each user and such user shall be solely responsible for any results, including but not limited to, any and all loss and damages incurred due to such uses. Users must implement and verify all testing and analyses for proving the safety and compatibility of final products that have been created or altered by using Sirmax's materials or products. The data and values inserted and/or contained in this document may be changed due to quality improvement of the product without any prior notification.